

▶ SparticGhard 200

ALIPHATIC POLYASPARTIC

▶ The Brand
You can Trust!

Ghemco SparticGhard 200 is an aliphatic polyaspartic, environmentally-friendly surface top coat for waterproofing membrane systems. SparticGhard 200 is quick curing and specifically formulated to be installed in thin film applications. Ghemco manufactures products in different VOC's ranging from 100 to 340 grams/liter to comply with VOC requirement in various regions. Make sure to use the right grade of product that complies with VOC regulations/requirements applicable as per federal, state, statutory, counties, cities and local bodies at the place of installation.

FEATURES & BENEFITS

- ▶ Quick Cure
- ▶ Very Durable
- ▶ High Tensile Strength
- ▶ High Gloss
- ▶ Abrasion Resistant
- ▶ Excellent Weatherability
- ▶ Seamless Waterproofing Membrane
- ▶ UV Resistant For Superior Gloss Retention

TYPICAL USES

- ▶ Concrete
- ▶ Plywood
- ▶ Cold Storage Areas
- ▶ Chemical Plants
- ▶ Fertilizer Plants
- ▶ Off-Shore Oil Platforms
- ▶ Steel
- ▶ Plastic
- ▶ Food Processing Areas
- ▶ Pulp and Paper Mills
- ▶ Pipeline Barges
- ▶ Industrial Warehouses

DIRECTION OF USE

Packaging

2 Gallon Kit: One 1 gallon (3.78 liters) can Side-A and One 1 gallon (3.78 liters) can Side-B
10 Gallon Kit: One 5 gallon (18.9 liter) pail of Side-A and One 5 gallon (18.9 liter) pail of Side-B
10-gallon kit is not a stock item and is available with minimum order of 100 gallons (378 liters)

Color

Clear and custom colors available.

Coverage

The approximate coverage is 1 gallon/100 sqft (0.41 l/sqm). Coverage rate will depend on surface roughness and porosity.

Surface Preparation

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Refer to product General Guidelines for detailed surface preparation information.

Minimum recommended surface preparation:

- METAL: SSPC-SP6/NACE 3, 2 mils (50 microns) profile
- CONCRETE & MASONRY: SSPC-SP13/NACE 6 or ICRI No. 310.2 CSP 3-5. Primer required.

▶ SparticGhard 200

ALIPHATIC POLYASPARTIC

▶ The Brand
You can Trust!

DIRECTION OF USE

Mixing

SparticGhard 200 may not be diluted under any circumstance. SparticGhard 200 Side A and Side B should be mixed individually before combining. Add Side B to Side A while mixing, using a mechanical mixer at medium speed. Mix until a homogeneous mixture and color is attained (at least 5 minutes) and mix frequently during application to maintain uniform color. Use care to scrape the sides of the container to ensure that no unmixed material remains. Use caution not to whip air into the material as this may result in pinhole blisters and/or shortened pot life. Do not mix in an up and down motion. Do not mix any material that cannot be used with 45 minutes.

Application

SparticGhard 200 can be applied by phenolic resin core roller, high pressure spray, or through a cup gun under low pressure. SparticGhard 200 should be applied at a minimum film thickness of 5 mils. It should be noted that the heavier the application, the longer the curing process takes.

Apply SparticGhard 200 evenly over the entire substrate. For best results, use an airless sprayer. A phenolic resin core roller may be used, but extra care should be taken not to cause air bubbles.

Curing

At 75°F (24°C) and 50% relative humidity, allow each coat to cure 2-4 hours. Allow 6 hours before permitting light pedestrian traffic and at least 24-48 hours before permitting heavy pedestrian traffic on to the finished surface. Uncured SparticGhard 200 is very sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Use caution in batch sizes and thickness of application. If more than 12 hours have passed after applying clear coat of SparticGhard 200, then re-prime surface with SPUR Primer and apply SparticGhard 200 pigmented coat. If clear coat is required, then clear coat should be applied only after pigmented coat. If clear coat is applied after primer, the primer will become yellowish with exposure to light and surface will not look aesthetically pleasing. Low temperature and/or low humidity extend the cure time.

Cleanup

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

Storage

SparticGhard 200 has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

SAFETY & PRECAUTIONS

Limitations

The following conditions must not be coated with Ghemco coatings or systems: split slabs, buried membrane, sandwich slabs with insulation, slabs over un-vented metal pan, magnesite, and non-structural lightweight concrete. On grade slabs may receive Ghemco system coatings provided a moisture-vapor transmission test is first performed. Please contact Ghemco's technical department with the results.

With regard to coating asphalt surfaces, please contact Ghemco's technical department. Surfaces must be dry, clean and free of foreign matter. Clear coating may turn opaque and cloudy due to moisture penetration, especially in exterior applications. Surface may be slippery when wet. Containers that have been opened must be used as soon as possible. Do not dilute under any circumstance.

Warning

This product contains Isocyanates and Solvent.

► SparticGhard 200

ALIPHATIC POLYASPARTIC

► The Brand
You can Trust!

TECHNICAL DATA

Mix Ratio by Volume	1A : 1B
Coverage Rate	1 gal / 100 sq ft (0.41 l / sq m)
Dry Film Thickness (per Coat)	14 ± 2 mils (356 ± 50µ)
Pot Life @ 75°F (24°C), 50% R.H.	40 - 45 minutes
Hardness, ASTM-2240	65 ± 5 Shore A
Tear Resistance, ASTM D-624	400 ± 20 pli (70.1 ± 8.8 kN/m)
Tensile Strength, ASTM D-412	3500 ± 300 psi (24.1 ± 2.1 MPa)
Ultimate Elongation, ASTM 412	50 ± 10%
Specific Gravity	Side A: 1.07 ± 0.1 / Side B: 1.02 ± 0.1
Total Solids, by Weight, ASTM D-2669	90 ± 2%
Total Solids, by Volume, ASTM D-2697	88 ± 2%
Viscosity @ 75°F (24°C)	Side A: 200 ± 50 cps / Side B: 200 ± 50 cps
VOC's, ASTM D-2369-81	0.83 lb / gal (100 gm / liter)

* This information is intended only as a guide for design purposes. The values shown are the average values obtained from sprayed laboratory samples. The test methods were performed per the ASTM Book of Standards. Higher or lower temperature & humidity conditions will affect dry time. The information contained herein is for purposes of identifying the product and does not constitute a warranty that the product will conform to that description. Product specifications and performance will vary depending on application methodologies, raw materials and other factors.

Please read all information in the general guidelines, technical data sheets, application guide, and safety data sheets (SDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local Ghemco Representative or visit our website for current technical data and instructions. DISCLAIMER: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and tests, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazards listed herein are the only ones that may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether verbal or in writing, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Ghemco makes no claim that these tests or any other tests, accurately represent all environments.