

▶ Accelerator

QUICK CURE ACCELERATOR FOR URETHANE BASE COATS

Ghemco Accelerator is a single component, proprietary liquid thickener/accelerator for Ghemco base membranes. This accelerator enhances the moisture curing characteristics that accelerates the cure time and causes the coating to thicken. Accelerator is designed to be used with Ghemco SolidGhard Base Coat, SolidGhard Base Coat SF, DuraGhard Base Coat, DuraGhard Supreme Base Coat, and SPUR Primer..

FEATURES & BENEFITS

- Creates a Thixotropic Compound
- Fast Cure Time
- Saves in Labor Cost - Apply Two Coats in One Day

DIRECTION OF USE

Typical Uses

- Creates a Caulking Compound for Plywood Joints, Cracks, Concrete Expansion Joints and Flashings
- Vertical Surfaces
- When Quick Access is Necessary

Mixing

Accelerator may be mixed into SolidGhard Base Coat, SolidGhard Base Coat SF, DuraGhard Base Coat, DuraGhard Supreme Base Coat, and SPUR Primer. Mix base membrane thoroughly then add and mix Accelerator into the base membrane until a homogeneous mixture and color is attained or for at least 5 minutes, if mixed by hand. Do not mix in an up and down motion.

The mixing ratio of Accelerator to base membrane is: 2 pints (or less) Accelerator to 1 gallon base membrane (0.24 liters Accelerator to 3.78 liters base membrane)

-OR-

1 quart (or less) Accelerator to 5 gallons base membrane (0.95 liters Accelerator to 18.9 liters base membrane)

The pot life of the resulting thixotropic compound is approximately 15 to 20 minutes at 75°F (24°C) and 50% relative humidity.

► Accelerator

QUICK CURE ACCELERATOR FOR URETHANE BASE COATS

► The Brand
You can Trust!

DIRECTION OF USE

Cleanup

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

Storage and Handling

Accelerator has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

SAFETY & PRECAUTIONS

Limitations

Excessive Accelerator will result in a reduction of the physical properties of the base membrane. Not UV stable. Cannot withstand direct wear or abrasion. Surfaces must be dry, clean and free of foreign matter. After mixing material must be used within 15-20 minutes. Do not dilute under any circumstance. Should use in a well ventilated area due to strong odor.

This product is considered Dangerous Goods. DOT regulations classify it as: UN 1760, CORROSIVE LIQUID N.O.S. (contains Amine), Class 8, PG-111. This product when comes in contact with water, will react violently and can cause a fire. Dispose all waste per applicable regulations.

Warning

This product contains Curatives.

► Accelerator

QUICK CURE ACCELERATOR FOR URETHANE BASE COATS

► The Brand
You can Trust!

TECHNICAL DATA

Color	Amber
Packaging	1 quart (0.95 liter) can / 1 gallon (3.78 liter) can
Pot Life @ 75°F (24°C), 50% RH	15 - 20 minutes
Mixing Ratio	Accelerator:Base Coat - 1:20
Specific Gravity	0.98 ± 0.05
Total Solids, by Weight	100%
Total Solids, by Volume	100%
Viscosity @ 75°F (24°C)	100 ± 50 cps
VOCs	0 lb/gal, 0 gm/liter

* This information is intended only as a guide for design purposes. The values shown are the average values obtained from sprayed laboratory samples. The test methods were performed per the ASTM Book of Standards. Higher or lower temperature & humidity conditions will affect dry time. The information contained herein is for purposes of identifying the product and does not constitute a warranty that the product will conform to that description. Product specifications and performance will vary depending on application methodologies, raw materials and other factors.

Please read all information in the general guidelines, technical data sheets, application guide, and safety data sheets (SDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local Ghemco Representative or visit our website for current technical data and instructions. DISCLAIMER: All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and tests, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazards listed herein are the only ones that may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether verbal or in writing, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Ghemco makes no claim that these tests or any other tests, accurately represent all environments.