

► DuraGhard Over Coat II Textured

ALIPHATIC POLYUREA WATERPROOFING TOP COAT

DuraGhard Over Coat II Textured is a two component, integrally textured, fast setting, rapid curing and solvent free, high solids, hybrid aliphatic polyurea elastomeric membrane. DuraGhard Over Coat II Textured can be applied to properly prepared interior or exterior concrete, plywood, and metal surfaces. It is suitable for single or multiple applications, in temperatures as low as 20°F (-6.67 C) and is insensitive to moisture. Ghemco manufactures products in different VOC's ranging from 100 to 340 gms/liter to comply with VOC requirements in various regions. Make sure to use the correct grade of product which complies with VOC regulations/requirements applicable as per federal, state, statutory, counties, cities and local bodies at the place of installation.

FEATURES & BENEFITS

- Environmentally Safe
- High Solids
- High Tensile Strength
- Meets USDA Criteria
- Non-Gassing
- Quick Cure
- Seamless
- UV Stable

TYPICAL USES

- Kennels
- Mechanical Room Floors
- Pedestrian Decks
- Vehicular Decks

DIRECTION OF USE

Coverage Rate

The approximate coverage is 1 gallon/78 sqft (0.49 l/sqm). Coverage rate will depend on surface roughness and porosity.

Mixing

Before application, pre-mix DuraGhard Over Coat II Textured Side A using a mechanical mixer at slow speed. Add Side B and continue mixing until a homogeneous mixture and color is attained. Use caution not to entrap air into the material as this may result in pinhole blisters and/or shortened pot life. Do not mix in an up and down motion.

Application

Apply DuraGhard Over Coat II Textured evenly over the entire deck using a 1/8" inch notched squeegee or notched trowel. With a 3/8"-1/2" inch nap phenolic core roller, uniformly back roll the product within the application area.

Requires a continuous coating application to minimize lines and/or streaking. Apply up to 1.28 gallons/100 sqft (4.85 liters/9.29 sqm) or 20 mils (508 microns) in a single application. To attain proper adhesion between coats, it is imperative that re-coating be done within 8-12 hours.

► DuraGhard Over Coat II Textured

► The Brand
You can Trust!

ALIPHATIC POLYUREA WATERPROOFING TOP COAT

DIRECTION OF USE

Curing

At 75°F (24°C) and 50% relative humidity, allow each coat to cure a minimum 2-4 hours. Cure time will vary depending on temperature and humidity. If more than 24 hours passes between coats, re-prime the surface with Ghemco SPUR Primer before proceeding.

Allow a minimum 16 hours before permitting light pedestrian traffic and at least 60 hours before permitting heavy pedestrian or vehicular traffic on the finished surface. Cure time will vary depending on temperature and humidity.

DuraGhard Over Coat II Textured is sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Use caution in batch sizes. Do not use Quick Cure Additive with DuraGhard Over Coat II Textured.

Cleanup

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

SAFETY & PRECAUTIONS

Storage

DuraGhard Over Coat II Textured has a shelf life of 1 year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

Limitations

The following conditions must not be coated with Ghemco deck coatings or systems: split slabs, buried membrane, sandwich slabs with insulation, slabs over unvented metal pan, magnesite, and non-structural lightweight concrete. On grade slabs may receive Ghemco system coatings provided a moisture-vapor transmission test is first performed. Please contact Ghemco's technical department with the results.

With regard to coating asphalt surfaces, please contact Ghemco's technical department.

Surfaces must be dry, clean and free of foreign matter. Clear coating may turn opaque and cloudy due to moisture penetration, especially in exterior applications. Surface may be slippery when wet. Containers that have been opened must be used as soon as possible. Do not dilute under any circumstance.

Warning

This product contains Isocyanates and Solvent.

DuraGhard Over Coat II Textured, Side-B is considered Dangerous Goods. DOT regulations classify it as: UN 1760, Corrosive Liquid, N.O.S. (Contains Amine), Class 8, PG III.

► DuraGhard Over Coat II Textured

► The Brand
You can Trust!

ALIPHATIC POLYUREA WATERPROOFING TOP COAT

TECHNICAL DATA

Color	Dolphin Grey and Tan. Custom colors available. Please speak with a Ghemco Representative.
Packaging	4.4 Gallon Kit; Side A: Pail (Net 4 Gallons, 15.4 Liters) / Side B: 0.5 Gallon Jar (Net 0.4 Gallons, 1.54 Liters)
Coverage Rate	1 gal/78 sq ft (0.49 l/sqm or 78 sq ft/gallon)
Dry Film Thickness	14 ± 2 mils (356 ± 50 microns)
Hardness, ASTM-2240	85 ± 5 Shore A
Tear Resistance, ASTM D624	300 ± 20 pli (52.6 ± 8.8 kN/m)
Tensile Strength ASTM D412	3200 ± 200 psi (22.1 ± 1.4 MPa)
Ultimate Elongation, ASTM D412	400 ± 50%
Moisture Vapor Transmission, ASTM E96	1.54 perms
Total Solids by Weight, ASTM D2669	88 ± 2%
Total Solids by Volume, ASTM D2697	87% ± 2%
Water Absorption, ASTM D471	1.3% by weight
VOC, ASTM D2369-81	< 0.5 lb/gal (< 60 gm/liters)

* This information is intended only as a guide for design purposes. The values shown are the average values obtained from sprayed laboratory samples. The test methods were performed per the ASTM Book of Standards. Higher or lower temperature & humidity conditions will affect dry time. The information contained herein is for purposes of identifying the product and does not constitute a warranty that the product will conform to that description. Product specifications and performance will vary depending on application methodologies, raw materials and other factors.

Please read all information in the general guidelines, technical data sheets, application guide, and safety data sheets (SDS) before applying material. Published technical data and instructions are subject to change with-out notice. Contact your local Ghemco Representative or visit our website for current technical data and instructions. **DISCLAIMER:** All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and tests, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazards listed herein are the only ones that may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether verbal or in writing, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Ghemco makes no claim that these tests or any other tests, accurately represent all environments.